



QUALITY SPECIFICATIONS

MEPDUAL (DUAL USE)

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE							
Nominal Basis Weight	g/m ²	T 410 om-13	90	100	110	120	130	140	160	
Nominal Moisture	%	T 412 om-16	8							
Burst Strength	kPa	T 403 om-15	200	225	250	290	320	345	390	
SCT _{CD}	kN/m	T 826 om-13	1.6	1.8	2.0	2.2	2.4	2.6	3.0	
CMT ₃₀	N	T 809 om-17	145	165	180	195	210	225	260	
COBB ₆₀ (Top Side)	g/m ²	T 441 om-13	40	35	35	35	35	35	35	
COBB ₆₀ (Bottom Side)	g/m ²	T 441 om-13	-	135	135	135	135	135	135	

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE							
Nominal Basis Weight	g/m ²	T 410 om-13	90	100	110	120	130	140	160	
Mean Basis Weight	%		± 2%	± 2%	± 2%	± 3%	± 3%	± 3%	± 3%	
Nominal Moisture	%	T 412 om-16	8							
Mean Moisture	%		± 1							
Burst Strength (minimum)	kPa	T 403 om-15	180	202	225	2.55	2.98	3.23	3.40	
SCT _{CD} (minimum)	kN/m	T 826 om-13	1.4	1.6	1.8	2	2.1	2.3	2.6	
CMT ₃₀ (minimum)	N	T 809 om-11	126	140	155	170	180	200	224	
COBB ₆₀ (Top Side) maximum	g/m ²	T 441 om-13	50							

PRODUCT INFORMATION

Reel Width, Preferably Trimmings As specified
 Reel Diameters, As specified
 Core Inside Diameter 100 – 100.2 mm
 Quantity Tolerance As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.
TESTING CONDITION: Temperature = 23 °C, Relative Humidity = 50%

Paper should not be stored near any flammable material.
 * Test Method = TAPPI

