



# QUALITY SPECIFICATIONS

## MEPFLUTE (HIGH PERFORMANCE FLUTING)

### TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE										
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-13	90	100	112	120	125	140	150	160	175	190	200
Nominal Moisture	%	T 412 om-16	8										
SCT <sub>CD</sub>	kN/m	T 826 om-13	1.60	1.80	2.0	2.2	2.3	2.5	2.7	2.9	3.2	3.4	3.6
CMT <sub>30</sub>	N	T 809 om-17	170	190	213	228	238	266	285	304	-	-	-
Water Drop Test	Sec	T 831 om-14	5 - 10										

### TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE										
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-13	90	100	112	120	125	140	150	160	175	190	200
Mean Basis Weight	%		± 3%										
Nominal Moisture	%	T 412 om-16	8										
Mean Moisture	%		± 1										
SCT <sub>CD</sub> (minimum)	kN/m	T 826 om-13	1.53	1.70	1.90	2.04	2.13	2.38	2.55	2.72	2.98	3.23	3.40
CMT <sub>30</sub> (minimum)	N	T 809 om-17	162	180	202	216	225	252	270	288	-	-	-

### PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified



### STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.  
**TESTING CONDITION:** Temperature = 23 °C, Relative Humidity = 50%

Paper should not be stored near any flammable material.  
 \* Test Method = TAPPI

