



QUALITY SPECIFICATIONS

MEPKRAFT (KRAFT TOP LINER)

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE							
Nominal Basis Weight	g/m ²	T 410 om-13	110	125	135	150	160	175	200	
Nominal Moisture	%	T 412 om-16	8							
Burst Strength	kPa	T 403 om-15	350	390	420	450	470	485	555	
SCT _{CD}	kN/m	T 826 om-13	2.10	2.40	2.60	2.80	3.00	3.30	3.75	
Roughness (Bendtsen)	ml/min	T 538 om-16	1200							
COBB ₆₀ (Top)	g/m ²	T 441 om-13	30							

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE							
Nominal Basis Weight	g/m ²	T 410 om-13	110	125	135	150	160	175	200	
Mean Basis Weight	%		± 3%							
Nominal Moisture	%	T 412 om-16	8							
Mean Moisture	%		± 1.0							
Burst Strength	kPa	T 403 om-15	308	350	378	410	430	465	515	
SCT _{CD}	kN/m	T 826 om-13	1.81	2.05	2.23	2.47	2.64	2.89	3.30	
Roughness (Bendtsen)	ml/min	T 538 om-16	1500							
COBB60 (Top)	g/m ²	T 441 om-13	50							

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified



STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

TESTING CONDITION: Temperature = 23 °C, Relative Humidity = 50%

Paper should not be stored near any flammable material.

* Test Method = TAPPI

