



QUALITY SPECIFICATIONS

MEPLAMINATE (ABSORBENT KRAFT)

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE
Nominal Basis Weight	g/m ²	T 410 om-13	140 150 160
Nominal Moisture	%	T 412 om-16	4.5
Wet Tensile Breaking Strength (CD)	N	T 456 om-15	4
Gurley	Sec	T 536 om-12	25
Water Absorption Test (Klemin Type)	mm	SCAN P 13:64	35
COBB ₆₀	g/m ²	T 441 om-13	250

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE
Nominal Basis Weight	g/m ²	T 410 om-13	140 150 160
Mean Basis Weight	%		± 3%
Nominal Moisture	%	T 412 om-16	4.5
Mean Moisture	%		± 1
Wet Tensile Breaking Strength (CD)	N	T 456 om-15	3.50
Gurley	Sec	T 536 om-12	40.00
Water Absorption Test (Klemin Type)	mm	SCAN P 13:64	30.00
COBB ₆₀	g/m ²	T 441 om-13	220

PRODUCT INFORMATION

Reel Width, Preferably Trimmings As specified
 Reel Diameters, As specified
 Core Inside Diameter Stretch Film Wrapped
 Quantity Tolerance As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.
TESTING CONDITION: Temperature = 23 °C, Relative Humidity = 50%

Paper should not be stored near any flammable material.
 * Test Method = TAPPI

