



# QUALITY SPECIFICATIONS

## MEPWHITE (WHITE TOP LINER)

### TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE					
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-13	125	140	150	160	175	200
Nominal Moisture	%	T 412 om-16	8					
Burst Strength	kPa	T 403 om-15	278	300	320	340	363	386
SCT <sub>CD</sub>	kN/m	T 826 om-13	1.87	2.10	2.25	2.40	2.62	2.95
Scott-Bond	J/m <sup>2</sup>	T 569 om-14	250					
Roughness (Bendtsen)	ml/min	T 538 om-16	700					
Brightness	%	T 452 om-08	80					
b*			-8.0					
COBB <sub>60 (Top)</sub>	g/m <sup>2</sup>	T 441 om-13	25 / 120					

### TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE					
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-13	125	140	150	160	175	200
Mean Basis Weight	%		± 3%					
Nominal Moisture	%	T 412 om-16	8					
Mean Moisture	%		± 1					
Burst Strength	kPa	T 403 om-15	250	270	288	306	327	347
SCT <sub>CD</sub>	kN/m	T 826 om-13	1.75	1.96	2.10	2.24	2.45	2.80
Scott-Bond	J/m <sup>2</sup>	T 569 om-14	Min. 200					
Roughness (Bendtsen)	ml/min	T 538 om-16	Max.900					
Brightness	%	T 452 om-08	80 ± 2					
b*			Min. -7.7 Max 8.3					
COBB <sub>60 (Top)</sub>	g/m <sup>2</sup>	T 441 om-13	45 / 150					

### PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified



### STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

**TESTING CONDITION:** Temperature = 23 °C, Relative Humidity = 50%

Paper should not be stored near any flammable material.

\* Test Method = TAPPI

