

## TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE					
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-98	125	140	150	160	175	200
Nominal Moisture	%	T 412 om-94	8%					
Burst Strength	kPa	T 403 om-97	278	300	320	340	363	386
SCT <sub>CD</sub>	kN/m	T 826 pm-92	1.80	2.00	2.15	2.30	2.45	2.75
Scott-Bond	J/m <sup>2</sup>	T 569 pm-00	250					
Roughness (Bendtsen)	ml/min	ISO 8791-2	1200					
Brightness	%	T 452 om-98	76					
b*			-7.5					
COBB <sub>60</sub>	g/m <sup>2</sup>	T 441 om-98 (Top/Bottom)	25/120					

## TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE					
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-98	125	140	150	160	175	200
Mean Basis Weight	%		± 3%					
Nominal Moisture	%	T 412 om-94	8					
Mean Moisture	%		± 1					
Burst Strength	kPa	T 403 om-97	250	270	288	306	327	
SCT <sub>CD</sub>	kN/m	T 826 pm-92	1.60	1.80	1.95	2.10	2.30	2.60
Scott-Bond	J/m <sup>2</sup>	T 569 pm-00	Min . 200					
Roughness (Bendtsen)	ml/min	ISO 8791-2	Max . 1500					
Brightness	%	T 452 om-98	76 ± 2					
b*			Min. -6.7					
COBB <sub>60</sub>	g/m <sup>2</sup>	T 441 om-98 (Top/Bottom)	45/150					

## PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified

## STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.
Testing Condition: Temperature = 1 ± 23 °C, Relative Humidity = 5 ± 50 % * Test Method = TAPPI



@  
Corrugated  
Recycles

