

TYPICAL CHARACTERISTICS

| PARAMETERS | UNIT | STANDARD METHOD | GRAMMAGE | | | | | |
|----------------------|------------------|--------------------------|----------|------|------|------|------|------|
| Nominal Basis Weight | g/m ² | T 410 om-98 | 125 | 140 | 150 | 160 | 175 | 200 |
| Nominal Moisture | % | T 412 om-94 | 8% | | | | | |
| Burst Strength | kPa | T 403 om-97 | 278 | 300 | 320 | 340 | 363 | 386 |
| SCT _{CD} | kN/m | T 826 pm-92 | 1.80 | 2.00 | 2.15 | 2.30 | 2.45 | 2.75 |
| Scott-Bond | J/m ² | T 569 pm-00 | 250 | | | | | |
| Roughness (Bendtsen) | ml/min | ISO 8791-2 | 1200 | | | | | |
| Brightness | % | T 452 om-98 | 76 | | | | | |
| b* | | | -7.5 | | | | | |
| COBB ₆₀ | g/m ² | T 441 om-98 (Top/Bottom) | 25/120 | | | | | |

TOLERANCE

| PARAMETERS | UNIT | STANDARD METHOD | GRAMMAGE | | | | | |
|----------------------|------------------|--------------------------|------------|------|------|------|------|------|
| Nominal Basis Weight | g/m ² | T 410 om-98 | 125 | 140 | 150 | 160 | 175 | 200 |
| Mean Basis Weight | % | | ± 3% | | | | | |
| Nominal Moisture | % | T 412 om-94 | 8 | | | | | |
| Mean Moisture | % | | ± 1 | | | | | |
| Burst Strength | kPa | T 403 om-97 | 250 | 270 | 288 | 306 | 327 | |
| SCT _{CD} | kN/m | T 826 pm-92 | 1.60 | 1.80 | 1.95 | 2.10 | 2.30 | 2.60 |
| Scott-Bond | J/m ² | T 569 pm-00 | Min . 200 | | | | | |
| Roughness (Bendtsen) | ml/min | ISO 8791-2 | Max . 1500 | | | | | |
| Brightness | % | T 452 om-98 | 76 ± 2 | | | | | |
| b* | | | Min. -6.7 | | | | | |
| COBB ₆₀ | g/m ² | T 441 om-98 (Top/Bottom) | 45/150 | | | | | |

PRODUCT INFORMATION

| | |
|----------------------------------|----------------|
| Reel Width, Preferably Trimmings | As specified |
| Reel Diameters, | As specified |
| Core Inside Diameter | 100 – 100.2 mm |
| Quantity Tolerance | As specified |

STORAGE RECOMMENDATION

| |
|---|
| Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material. |
| Testing Condition: Temperature = 1 ± 23 °C, Relative Humidity = 5 ± 50 % * Test Method = TAPPI |



@
Corrugated
Recycles

