

## TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-98	140
Nominal Moisture	%	T 412 om-94	150
Wet Tensile Breaking Strength (CD)	N	T 456 om-03	4.5
Gurley	Sec	T 536 om-96	4
Water Absorption Test (Klemn Type)	mm	SCAN P 13:64	25
COBB <sup>60</sup>	g/m <sup>2</sup>	T 441 om-98	35
			250

## TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-98	140
Mean Basis Weight	%		150
Nominal Moisture	%	T 412 om-94	± 3%
Mean Moisture	%		4.5
Wet Tensile Breaking Strength (CD)	N	T 456 om-03	± 1
Gurley	Sec	T 536 om-96	3.5
Water Absorption Test (Klemn Type)	mm	SCAN P 13:64	40
COBB <sup>60</sup>	g/m <sup>2</sup>	T 441 om-98	30
			220

## PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters	As specified
Packing	Stretch Film Wrapped
Quantity Tolerance	As specified

## STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.
Testing Condition: Temperature = 1 ± 23 °C, Relative Humidity = 5 ± 50 % * Test Method = TAPPI



@  
Corrugated  
Recycles

