

## TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE				
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-98	112	127	140	150	160
Nominal Moisture	%	T 412 om-94			8.00		
SCT <sub>CD</sub>	kN/m	T 826 pm-92	2.15	2.45	2.70	2.80	3.05
CMT <sub>30</sub>	N	T 809 om-99	240	268	295	325	340
Wet Tensile Strength (MD)	N	T 456 om-87	11	12	12	12	12
COBB <sub>60</sub>	g/m <sup>2</sup>	T 441 om-98			50		

## TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE				
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-98	112	127	140	150	160
Mean Basis Weight	%				± 3%		
Nominal Moisture	%	T 412 om-94			8.0		
Mean Moisture	%				-0.5 / + 1		
SCT <sub>CD</sub> (minimum)	kN/m	T 826 pm-92	1.95	2.20	2.40	2.60	2.75
CMT <sub>30</sub> (minimum)	N	T 809 om-99	213	241	266	285	304
Wet Tensile Strength (MD)	N	T 456 om-87			9		
COBB <sub>60</sub>	g/m <sup>2</sup>	T 441 om-98			55		

## PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified

## STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.
Testing Condition: Temperature = 1 ± 23 °C, Relative Humidity = 5 ± 50 % * Test Method = TAPPI



@  
Corrugated  
Recycles

