

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Nominal Basis Weight	g/m ²	T 410 om-98	110	125	135	150	160	200	
Nominal Moisture	%	T 412 om-94	8.0						
Burst Strength	kPa	T 403 om-97	350	390	420	450	470	555	
SCT _{CD}	kN/m	T 826 pm-92	1.85	2.00	2.20	2.40	2.60	3.25	
Roughness (Bendtsen)	ml/min	ISO 8791-2	1200						
COBB ₆₀ (Top)	g/m ²	T 441 om-98	30						

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Nominal Basis Weight	g/m ²	T 410 om-98	110	125	135	150	160	200	
Mean Basis Weight	%		± 3%						
Nominal Moisture	%	T 412 om-94	8.0						
Mean Moisture	%		± 1						
Burst Strength	kPa	T 403 om-97	300	350	375	405	425	500	
SCT _{CD}	kN/m	T 826 pm-92	1.60	1.81	1.96	2.18	2.32	2.90	
Roughness (Bendtsen)	ml/min	ISO 8791-2	1500						
COBB ₆₀ (Top)	g/m ²	T 441 om-98	50						

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.
Testing Condition: Temperature = 1 ± 23 °C, Relative Humidity = 5 ± 50 % * Test Method = TAPPI

