

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Nominal Basis Weight	g/m ²	T 410 om-98	90	100	110	120	130	140	160
Nominal Moisture	%	T 412 om-94				8			
Burst Strength	kPa	T 403 om-97	200	225	250	290	320	345	390
SCT _{CD}	kN/m	T 826 pm-92	1.6	1.8	2.0	2.2	2.4	2.6	3.0
CMT ₃₀	N	T 809 om-99	145	165	180	195	210	225	260
COBB ₆₀ (Top Side)	g/m ²	T 441 om-98	40	35	35	35	35	35	35
COBB ₆₀ (Bottom Side)	g/m ²	T 441 om-98	-	135	135	135	135	135	135

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE						
Nominal Basis Weight	g/m ²	T 410 om-98	90	100	110	120	130	140	160
Mean Basis Weight	%		± 2%	± 2%	± 2%	± 3%	± 3%	± 3%	± 3%
Nominal Moisture	%	T 412 om-94				8			
Mean Moisture	%					± 1			
Burst Strength (minimum)	kPa	T 403 om-97	180	202	225	260	288	310	350
SCT _{CD} (minimum)	kN/m	T 826 pm-92	1.4	1.6	1.8	2.0	2.1	2.3	2.6
CMT ₃₀ (minimum)	N	T 809 om-99	126	140	155	170	180	200	224
COBB ₆₀ (Top Side) maximum	g/m ²	T 441 om-98				50			

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.
Testing Condition: Temperature = 1 ± 23 °C, Relative Humidity = 5 ± 50 % * Test Method = TAPPI

