

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD	GRAMMAGE							
			200	250	300	350	400	450	500	550
Nominal Basis Weight	g/m ²	T 410 om-98	200	250	300	350	400	450	500	550
Nominal Moisture	%	T 412 om-94	7							
Thickness	µm		310	388	465	543	620	698	775	853
Bulk	cc/g		1.55							
Internal Bond (Scotte type)	j/m ²	T 569 pm-00	200							
COBB 60	g/m ²	T 441 om-98	400							

TOLERANCE

PARAMETERS	UNIT	STANDARD	GRAMMAGE							
			200	250	300	350	400	450	500	550
Nominal Basis Weight	g/m ²	T 410 om-98	200	250	300	350	400	450	500	550
Mean Basis Weight	%		± 3 %							
Nominal Moisture	%	T 412 om-94	7							
Mean Moisture	%		± 1 %							
Thickness	µm		± 30 µm							
Bulk	cc/g		± 0.05							
Internal Bond (Scotte type)	j/m ²	T 569 pm-00	Not less than 200 j/m ²							
COBB 60	g/m ²	T 441 om-98	500							

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	As specified
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 5% * Test Method = TAPPI



TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD	GRAMMAGE						
Nominal Basis Weight	g/m ²	T 410 om-98	200	250	300	350	400	450	500
Nominal Moisture	%	T 412 om-94	7						
Thickness	µm		310	388	465	543	620	698	775
Bulk	cc/g		1.55						
Internal Bond (Scotte type)	j/m ²	T 569 pm-00	350						
COBB 60	g/m ²	T 441 om-98	450						

TOLERANCE

PARAMETERS	UNIT	STANDARD	GRAMMAGE						
Nominal Basis Weight	g/m ²	T 410 om-98	200	250	300	350	400	450	500
Mean Basis Weight	%		± 3 %						
Nominal Moisture	%	T 412 om-94	7						
Mean Moisture	%		± 1 %						
Thickness	µm		± 35 µm						
Bulk	cc/g		± 0.05						
Internal Bond (Scotte type)	j/m ²	T 569 pm-00	Not less than 350 j/m ²						
COBB 60	g/m ²	T 441 om-98	500						

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	As specified
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated. Paper should not be stored near any flammable material.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 5% * Test Method = TAPPI



@
Corrugated
Recycles

