



QUALITY SPECIFICATIONS

MEPLINER (TESTLINER-2)

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE										
Nominal Basis Weight	g/m ₂	T 410 om-13	90	100	112	120	125	140	145	150	160	175	200
Nominal Moisture	%	T 412 om-16	8										
Burst Strength	kPa	T 403 om-15	225	250	280	300	312	350	363	375	400	437	500
SCT _{CD}	kN/m	T 826 om-13	1.53	1.65	1.85	2.00	2.05	2.30	2.40	2.50	2.65	2.90	3.30
COBB ₆₀ (Top)	g/m ₂	T 441 om-13	40										

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE										
Nominal Basis Weight	g/m ²	T 410 om-13	90	100	112	120	125	140	145	150	160	175	200
Mean Basis Weight	%		± 3%										
Nominal Moisture	%	T 412 om-16	8										
Mean Moisture	%		± 1										
Burst Strength	kPa	T 403 om-15	200	220	247	264	275	308	319	330	352	385	440
SCT _{CD}	kN/m	T 826 om-13	1.40	1.55	1.74	1.86	1.94	2.17	2.25	2.33	2.48	2.71	3.10
COBB ₆₀ (Top)	g/m ²	T 441 om-13	55										

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified



STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

TESTING CONDITION: Temperature = 23 °C, Relative Humidity = 50%

Paper should not be stored near any flammable material.

* Test Method = TAPPI

