

QUALITY SPECIFICATIONS



MEPCORE (CORE BOARD)

TYPICAL CHARACTERISTICS

GRADE -----▶▶			450X			500X			600X			700X			800X		
PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE		
Nominal Basis Weight	g/m ²	T 410 om-19	400	450	500	400	450	500	400	450	500	400	450	500	400	450	500
Nominal Moisture	%	T 412 om-22	6			6			6			6			6		
Thickness	μm	T 411 om-21	620	698	775	620	698	775	620	698	775	620	698	775	620	698	775
Bulk	cc/g		1.55			1.55			1.55			1.55			1.55		
Internal Bond (Scott type)	j/m ²	T 569 om-22	450			500			600			700			800		
COBB ₆₀	g/m ²	T 441 om-20	450	500		450	500		450	500		450	500		450	500	

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE			GRAMMAGE		
Nominal Basis Weight	g/m ²	T 410 om-19	400	450	500	400	450	500	400	450	500	400	450	500	400	450	500
Mean Basis Weight	%		± 3 %			± 3 %			± 3 %			± 3 %			± 3 %		
Nominal Moisture	%	T 412 om-22	6			6			6			6			6		
Mean Moisture	%		± 1 %			± 1 %			± 1 %			± 1 %			± 1 %		
Thickness	μm	T 411 om-21	± 40 μm			± 40 μm			± 40 μm			± 40 μm			± 40 μm		
Bulk	cc/g		± 0.08			± 0.08			± 0.08			± 0.08			± 0.08		
Internal Bond (Scott type)	j/m ²	T 569 om-22	Min 450 j/m ² , Max 500 j/m ²			Min 500 j/m ² , Max 600 j/m ²			Min 600 j/m ² , Max 700 j/m ²			Min 700 j/m ² , Max 800 j/m ²			Min 800 j/m ² , Max 900 j/m ²		
COBB ₆₀	g/m ²	T 441 om-20	650	750		650	750		650	750		650	750		650	750	

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	As specified
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

* Test Method = TAPPI