



Middle East Paper Company  
شركة الشرق الأوسط لصناعة وإنتاج الورق

# QUALITY SPECIFICATIONS



## MEPKRAFT (KRAFT TOP LINER)

### TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE								
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-19	110	125	135	150	160	175	200	250	300
Nominal Moisture	%	T 412 om-22					8.0				
Burst Strength	kPa	T 403 om-22	350	390	420	450	470	485	555	660	700
SCT <sub>CD</sub>	kN/m	T 826 om-21	2.10	2.40	2.60	2.80	3.00	3.30	3.75	4.15	4.80
Roughness (Bendtsen)	ml/min	ISO 8791-2					1200				
COBB <sub>60</sub> (Top)	g/m <sup>2</sup>	T 441 om-21					30				
COBB <sub>60</sub> (Bottom)	g/m <sup>2</sup>	T 441 om-21					35				

### TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	GRAMMAGE								
Nominal Basis Weight	g/m <sup>2</sup>	T 410 om-19	110	125	135	150	160	175	200	250	300
Mean Basis Weight	%						± 3%				
Nominal Moisture	%	T 412 om-22					8.0				
Mean Moisture	%						± 1				
Burst Strength	kPa	T 403 om-22	308	350	378	410	430	465	515	610	650
SCT <sub>CD</sub>	kN/m	T 826 om-21	1.81	2.05	2.23	2.47	2.64	2.89	3.30	3.65	4.35
Roughness (Bendtsen)	ml/min	ISO 8791-2					1500				
COBB <sub>60</sub> (Top)	g/m <sup>2</sup>	T 441 om-21					50				
COBB <sub>60</sub> (Bottom)	g/m <sup>2</sup>	T 441 om-13					60				

### PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified

### STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

**Testing Condition:** Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

\* Test Method = TAPPI



**ISEGA**



FSC  
www.fsc.org  
FSC® C124131  
The mark of responsible forestry