

QUALITY SPECIFICATIONS



MEPLAMINATE (ABSORBENT KRAFT)

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD		GRAMMAGE	
Nominal Basis Weight	g/m ²	T 410 om-19	140	150	160
Nominal Moisture	%	T 412 om-22		4.5	
Wet Tensile Breaking Strength (CD)	N	T 456 om-22		4	
Wet Tensile Breaking Strength (MD)	N	T 456 om-22		9	
Gurley	Sec	T 460 om-21		25	
Water Absorption Test (Klemn Type)	mm	SCAN P 13:64		35	
COBB ₆₀	g/m ²	T 441 om-20		250	

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD		GRAMMAGE	
Nominal Basis Weight	g/m ²	T 410 om-19	140	150	160
Mean Basis Weight	%			± 3%	
Nominal Moisture	%	T 412 om-22		4.5	
Mean Moisture	%			± 1	
Wet Tensile Breaking Strength (CD)	N	T 456 om-22		3.5	
Wet Tensile Breaking Strength (MD)	N	T 456 om-22		7	
Gurley	Sec	T 460 om-21		40	
Water Absorption Test (Klemn Type)	mm	SCAN P 13:64		30	
COBB ₆₀	g/m ²	T 441 om-20		220	

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters	As specified
Packing	Stretch Film Wrapped
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

* Test Method = TAPPI



ISEGA



The mark of responsible forestry