

QUALITY SPECIFICATIONS



MEPLINER (TESTLINER-2)

TYPICAL CHARACTERISTICS

| PARAMETERS | UNIT | STANDARD METHOD | GRAMMAGE | | | | | | | | | | | | | | |
|--------------------------|------------------|-----------------|----------|------|------|------|------|-----------|------|------|------|------|------|-------------|--|--|--|
| | | | 90 | 100 | 112 | 120 | 125 | 140 | 145 | 150 | 160 | 175 | 200 | 250 | | | |
| Nominal Basis Weight | g/m ² | T 410 om-19 | | | | | | | | | | | | | | | |
| Nominal Moisture | % | T 412 om-22 | | | | | | | 8 | | | | | | | | |
| Burst Strength | kPa | T 403 om-22 | 225 | 250 | 280 | 300 | 312 | 350 | 363 | 375 | 400 | 437 | 500 | 580 | | | |
| SCT _{CD} | kN/m | T 826 om-21 | 1.53 | 1.65 | 1.85 | 2.00 | 2.05 | 2.30 | 2.40 | 2.50 | 2.65 | 2.90 | 3.30 | 4.13 | | | |
| COBB _{60 (Top)} | g/m ² | T 441 om-20 | | | | | | 30 | | | | | | | | | |

TOLERANCE

| PARAMETERS | UNIT | STANDARD METHOD | GRAMMAGE | | | | | | | | | | | | | | |
|--------------------------|------------------|-----------------|----------|------|------|------|------|------|-------|------|------|------|------|-------------|--|--|--|
| | | | 90 | 100 | 112 | 120 | 125 | 140 | 145 | 150 | 160 | 175 | 200 | 250 | | | |
| Nominal Basis Weight | g/m ² | T 410 om-19 | | | | | | | ± 3% | | | | | | | | |
| Mean Basis Weight | % | | | | | | | | 8 | | | | | | | | |
| Nominal Moisture | % | T 412 om-22 | | | | | | | ± 1.0 | | | | | | | | |
| Mean Moisture | % | | | | | | | | | | | | | | | | |
| Burst Strength | kPa | T 403 om-22 | 200 | 220 | 247 | 264 | 275 | 308 | 319 | 330 | 352 | 385 | 440 | 520 | | | |
| SCT _{CD} | kN/m | T 826 om-21 | 1.40 | 1.55 | 1.74 | 1.86 | 1.94 | 2.17 | 2.25 | 2.33 | 2.48 | 2.71 | 3.10 | 3.88 | | | |
| COBB _{60 (Top)} | g/m ² | T 441 om-20 | | | | | | 55 | | | | | | | | | |

PRODUCT INFORMATION

| | |
|----------------------------------|----------------|
| Reel Width, Preferably Trimmings | As specified |
| Reel Diameters, | As specified |
| Core Inside Diameter | 100 – 100.2 mm |
| Quantity Tolerance | As specified |

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

* Test Method = TAPPI.



ISEGA



The mark of responsible forestry