

QUALITY SPECIFICATIONS



MEPWHITE (WHITE TOP TESTLINER)

TYPICAL CHARACTERISTICS

PARAMETERS	UNIT	STANDARD METHOD	125	140	150	160	175	200	
Nominal Basis Weight	g/m ²	T 410 om-19	125	140	150	160	175	200	
Nominal Moisture	%	T 412 om-22				7.50%			
Burst Strength	kPa	T 403 om-22	278	300	320	340	363	386	
SCT _{CD}	kN/m	T 826 om-21	1.87	2.10	2.25	2.40	2.62	2.95	
Internal Bond (Scott type)	J/m ²	T 569 om-22				250			
Roughness (Bendtsen)	ml/min	ISO 8791-2		600			600		
Brightness	%	T 452 om-18				80			
b*	-	-				-8.0			
COBB ₆₀	g/m ²	T 441 om-20		(Top/Bottom)				25/100	

TOLERANCE

PARAMETERS	UNIT	STANDARD METHOD	125	140	150	160	175	200
Nominal Basis Weight	g/m ²	T 410 om-19	125	140	150	160	175	200
Mean Basis Weight	%					± 3%		
Nominal Moisture	%	T 412 om-22				7.5		
Mean Moisture	%					± 1		
Burst Strength	kPa	T 403 om-22	250	270	288	306	327	347
SCT _{CD}	kN/m	T 826 om-21	1.75	1.96	2.10	2.24	2.45	2.80
Internal Bond (Scott type)	J/m ²	T 569 om-22				Min. 225		
Roughness (Bendtsen)	ml/min	ISO 8791-2		Max.800				Max. 900
Brightness	%	T 452 om-18				80 ± 2		
b*						Min. -7.7 Max 8.3		
COBB ₆₀	g/m ²	T 441 om-20		(Top/Bottom)				45/150

PRODUCT INFORMATION

Reel Width, Preferably Trimmings	As specified
Reel Diameters,	As specified
Core Inside Diameter	100 – 100.2 mm
Quantity Tolerance	As specified

STORAGE RECOMMENDATION

Paper should be stored in a cool & dry place which is covered and ventilated.

Testing Condition: Temperature = 23 ± 1 °C, Relative Humidity = 50 ± 2%

Paper should not be stored near any flammable material.

* Test Method = TAPPI



ISEGA



The mark of responsible forestry